

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: **81305382.4**

(51) Int. Cl.³: **C 25 B 11/10**
C 25 B 1/26, C 25 C 7/02

(22) Date of filing: **13.11.81**

(30) Priority: **26.11.80 GB 8037933**

(43) Date of publication of application: **02.06.82 Bulletin 82/22**

(84) Designated Contracting States:
BE DE FR GB IT NL SE

(71) Applicant: **IMI KYNOCH LIMITED**
Kynoch Works
Witton Birmingham B6 7BA(GB)

(72) Inventor: **Steele Hayfield, Peter Charles**
Church Garth St. Peter's Lane
Bickenhill Solihull West Midlands B910DR(GB)

(74) Representative: **Smith, Rex Clise et al,**
IMI LIMITED Patents and Licensing Department Kynoch
Works
Witton Birmingham B6 7BA(GB)

(54) **Electrode, method of manufacturing an electrode and electrolytic cell using such an electrode.**

(57) **An electrode particularly useful in hypochlorite cells operating at low temperatures or in metal winning cells in which the electrode comprises a titanium substrate with a platinum metal coating and an intermediate coating of substoichiometric tantalum oxide.**

EP 0 052 986 A1

- ii heat treating the layer in a vacuum or in a non-oxidising atmosphere, said atmosphere being substantially hydrogen-free, at a temperature and for a time sufficient for the titanium partially to reduce the oxide,
- 5 iii applying to the oxide layer a layer of an anodically active material.

The layer of oxide may be titanium oxide, deposited on the surface of the titanium by immersing the titanium surface into an acid solution containing trivalent titanium cations, maintaining the solution at a temperature in excess of 75°C and rendering the titanium surface anodic with respect to a cathode to anodically oxidise the titanium cations to form titanium oxide which is deposited onto the titanium surface as an adherent porous titanium oxide layer.

Alternatively the oxide may be tantalum oxide formed by applying a paint of a tantalum-containing compound to the surface and heating the surface in air or an oxygen-containing atmosphere to convert the compound to an oxide of tantalum.

The anodically active coating may contain a platinum group metal or oxide or an alloy or mixture of platinum group metals or oxides.

The platinum group metal, oxide, alloy or mixture may be applied by a route selected from the group:

- i applying a paint containing an organic or inorganic compound of the platinum group metal(s) to the surface and heating in air or an oxygen-containing atmosphere at a temperature in the range 350°C to 650°C to convert the compound to the metal(s) or oxide(s)

fail by reason of detachment of the anodically active surface and its falling off the anode rather than electrochemical wear of the anodically active material itself. Two particular applications for anodically active coated titanium in which this detachment is a problem are:

- 1 the operation of a hypochlorite cell at low temperatures (below 10°C); and
- 2 the use of an anode in zinc winning from a zinc sulphate solution.

As will be explained in more detail below there are particular problems associated with the operation of hypochlorite cells at temperatures below 10°C and also there are problems in providing an economically viable anode for use in metal winning operations where such anode is based on a coated titanium substrate.

The present invention is concerned with an electrode which has improved operating characteristics under the circumstances where the anodically active material is liable to become detached. It should be pointed out that in many cases it is not understood why the anodically active material becomes detached nor why the invention as set out below leads to an improvement in properties of the electrode.

By the present invention there is provided a method of manufacturing an electrode for use in an electrolytic cell, which method includes the steps of forming on the surface of a titanium substrate a coating by:

- i forming a layer of an oxide of a metal chosen from the group titanium, tantalum, zirconium, hafnium and niobium on the titanium surface

ii electroplating the platinum group metal onto
the oxide layer or onto a previously applied
painted and fired platinum group metal layer.

The present invention further provides an
5 electrode for electrochemical processes comprising a
substrate of titanium or an alloy thereof, an
intermediate coating of sub-stoichiometric tantalum
oxide and an outer layer of anodically active
material. The anodically active material may be a
10 coating containing a platinum group metal or oxide or
an alloy or mixture of platinum group metals or
oxides.

The present invention yet further provides an
electrochemical cell including an anode and a cathode
15 surrounded by an electrolyte wherein the anode
comprises an electrode manufactured by a method as set
out above or is an electrode of the type set out
above.

The electrochemical cell is preferably a
20 hypochlorite cell adapted and arranged to generate
sodium hypochlorite from an aqueous sodium chloride
solution, particularly adapted for operation and
capable of operation at temperatures of 10°C or below.

Alternatively the electrochemical cell may
25 include an electrolyte of an acidified sulphate
solution, particularly a solution containing ions of a
metal chosen from the group zinc, copper, nickel or
cobalt.

The coated titanium surface may be heated in a
30 vacuum at a temperature in the range 500°C to 1 000°C
for a time in excess of 5 minutes, preferably in the
range 5 minutes to 168 hours. The temperature is
preferably in the range 700°C to 850°C.

The titanium is preferably pretreated before coating with the tantalum-containing compound to remove any surface oxide on the surface of the titanium. The tantalum-containing compound may be a
5 tantalum resinate or an inorganic tantalum compound contained in an organic carrier.

The present invention particularly provides an electrochemical cell for the generation of sodium hypochlorite from an aqueous sodium chloride solution,
10 the cell comprising an anode and a cathode wherein the anode is an electrode of the type set out above or the anode is manufactured by the method set out above.

The present invention also provides a method of operating an electrochemical cell for the
15 generation of sodium hypochlorite from an aqueous sodium chloride solution which comprises operating an electrochemical cell of the type set out above and supplying to the cell an aqueous sodium chloride solution at temperatures of 10°C or below.

The present invention yet further provides a method of electrowinning a metal from a solution of the metal which comprises the steps of inserting into the solution containing ions of the metal an anode and a cathode and passing an electrical current between
20 the anode and the cathode so as to deposit the metal on the cathode wherein the improvement comprises using as an anode an electrode of the type set out above or an electrode manufactured by the method set out above.

By way of example embodiments of the present
30 invention will now be described with reference to the accompanying drawings which are graphs of precious metal loading against time.

Table Ia

Sample No	Precoat Loading (g/m ²)			Air HT 500°C/ lhr	Vac HT (°C/hr)	TNBT Loading (g/m ²)	Vac HT (°C/hr)	TNBT Loading (g/m ²)	Ir Loading (g/m ²)	PHT 400°C/ 20hrs
	1st	2nd	3rd							
ZLX									5.2	✓
ZLY	13.5	13.6	17.7	✓	750/1				4.7	✓
WD21(A)	13.8	14.0	11.3	✓	750/1				5.2	✓
WD21(B)	13.8	14.0	11.3	✓	800/1				5.3	✓
ZLZ	24.4	22.0	-	✓	750/1	33.3	750/1	-	6.6	✓
ZLZ(1)	24.4	22.0		✓	750/1	33.3	750/1	5.8	7.3	✓
ZMA	15.0	14.0	2.0	✓	750/1	30.6	750/1	-	6.6	✓
ZMB	13.0	22.0	-	✓	750/1	32.0	800/1	-	6.5	✓
ZMC	15.0	15.0	17.0	✓	750/1	31.0	800/1	-	6.3	✓
ZMC(1)	15.0	15.0	17.0	✓	750/1	31.0	800/1	5.0	6.7	✓

A sheet of commercial purity titanium was etched in 10% oxalic acid for a time between 8 and 16 hours. The titanium sheet was then immersed in a 7wt% sulphuric acid solution containing 5g/l of titanium as Ti^{3+} ions. The titanium sheet was connected as an anode relative to a lead cathode and a potential of 12v was applied. The anode current density was maintained in the region of $60A/m^2$. The solution was maintained at $80^{\circ}C$. A coating of titanium dioxide was deposited upon the titanium sheet at a rate of approximately $2g/m^2/hr$.

Coating was continued for a period of $7\frac{1}{2}$ hours to produce an overall coating loading of $15g/m^2$.

After coating the titanium sheet was washed in water and dried and a white titanium oxide coating was found to be firmly adherent to the titanium substrate.

The titanium substrate with the titanium dioxide coating was then transferred to a vacuum furnace and heated in a vacuum at a temperature of $750^{\circ}C$ for 6 hours. On cooling and removal of the sample from the furnace it was found that the sample had become black. This technique is the basis of the manufacture of a series of ten samples which were prepared and utilised as anodes in an acid solution containing 165g/l H_2SO_4 115ppm chloride and 5ppm fluoride. Details of the samples are given in Tables Ia and Ib below.

post heat treatment. The anode over-potentials at 35°C are in millivolts at a current density of 666A/m² and 3 000A/m².

5 The durability of the anodes is most clearly seen in Figures 1 and 2. In the figures, t is time in days and g/m² is applied noble metal coating in g/m². Anode samples ZLX exhibited high overpotential (H) after 13 days or, at a maximum, 27 days when the temperature was 35°C. At 60°C a high overpotential
10 occurred almost immediately. By comparison, however, it can be seen that anodes manufactured with substrates in accordance with the invention had vastly increased lives and sample ZMA was still continuing to operate after 260 days at 60°C. Improvements of this
15 magnitude are obviously very significant. It can be seen, therefore, that the material improvement in useful life of the anodes manufactured in accordance with the present invention would lead to economically more viable anodes being prepared, whereas with the
20 anodes without the corrosion resistant coating the short life of the anodes would make them lessviable. It will be appreciated that operation of an electrode in an acidified sulphate solution corresponds to metal winning, as far as the anode is concerned.

25 It has also been discovered that electrodes having an oxide interlayer in accordance with the invention are more resistant to cathodic degradation. Frequently it is found that if coated titanium anodes become cathodic, for example in an electrowinning cell
30 during shut down, the coating of precious metal can be undermined loosened and may fall off. Anodes having an interlayer, particularly of the ZLY or WD21 A or B type, have a much greater resistance to degradation in these circumstances.

35 A hypochlorite cell essentially comprises a series of anodes and cathodes immersed in a brine

Table Ib

5	Sample No	Anode Overpotentials in H ₂ SO ₄ (MV)	
		At 666A/m ²	At 3kA/m ²
	ZLX	435	520
	ZLY	445	545
	WD21(A)	460	565
10	WD21(B)	485	700
	ZLZ	435	650
	ZLZ(1)	530	700
	ZMA	460	615
15	ZMB	445	630
	ZMC	375	500
	ZMC(1)	545	680

20 In Table I the precoat loading refers to the titanium oxide loading applied in accordance with the method set out above. Where two or more precoat loadings are shown, the first coat was subsequently given a heat treatment at 150°C in air and the second

25 coat would be applied thereafter. Where three coats are applied the second coat would merely be dried out prior to the application of a third coat. In the column headed "vacuum heat treatment" the number prior to the slash refers to the temperature in °C and the

30 number after the slash refers to the time in hours. The reference to "TNBT loading" is to the loading of tetra-n-butyl titanate applied to the already reduced titanium oxide coating. The reference to "PHT" is

- A Utilising 70/30 platinum/iridium coated titanium electrodes operating at a current density of approximately 2 500A/m² initial loading 30.8g/m² platinum iridium:
- 5 after 286 hours - 16.3g/m²
 after 714 hours - 18.2g/m²
 after 972 hours - 16.2g/m²
 after 1 008 hours - zero - electrode failed by coating undermining.
- 10 B The platinum electroplate manufactured in accordance with the route set out in British Patent 1 351 741 failed after 3 000 hours of operation in brine at 5°C with a failure resulting from loss of coating adhesion.
- 15 C Ruthenium oxide coated titanium manufactured in accordance with the route set out in Example 5 of British Patent 1 327 760 produced products which failed after 80 hours and 200 hours in duplicate tests in brine at 5°C.
- 20 D Ruthenium oxide applied to titanium produced anodes which failed in brine at 5°C after 120 hours.
- 25 E By comparison electrodes in accordance with the present invention were manufactured by etching in oxalic acid a sheet of titanium and coating the sheet with 11g/m² of tantalum oxide by applying tantalum as a tantalum pentachloride paint in an alcohol. This coated titanium was then heated at 500°C in
- 30 air and was then vacuum annealed for one hour at 800°C. Subsequently 22.4g/m² of platinum-iridium were applied by painting a series of coats of a platinum-iridium containing paint onto the substrate and firing in air between each painted layer.

solution and electrically connected so as to pass current between them. The cell functions to generate sodium hypochlorite by anodic oxidation and cathodic reduction of the sodium chloride and a resultant
5 immediate recombination of the ionic species formed at the electrodes so as to form sodium hypochlorite. Such cells are in commercial use to generate sodium hypochlorite from seawater and other brine solutions. Conventionally the anodes used comprise platinum group
10 metal coated titanium.

It has long been known that low temperature inlet seawater (10°C or less) has an adverse effect on the durability of platinised titanium type electrodes in sodium hypochlorite. This problem first arose in
15 the early 1960s. The phenomenon is associated with the loss of platinum adhesion and peeling. The problems of operation of hypochlorite electrolyzers at low temperatures have become widely disseminated since that time. The leading manufacturer of ruthenium
20 oxide coated electrodes advised that their electrolyzers should not be operated with seawater at temperatures below 10°C. IMI Marston Limited, another leading manufacturer of electrodes, in this case titanium electrodes with a platinum-iridium containing
25 coating, also advise that the electrodes should not be operated in seawater at temperatures below 10°C. It appears that the coating on a titanium substrate does not wear but becomes undermined, presumably resulting from some activation of the titanium. It is not known
30 why titanium, so corrosion resistant towards seawater in normal cases, should have a weakness when polarised in hypochlorite cells with seawater at 5°C as opposed to 15°C. Tests carried out on an electrolyser to manufacture sodium hypochlorite from 3% brine gave the
35 following results:

5 The material was evaluated in a laboratory hypochlorite electrolyser at a current density of approximately 2 500A/m² utilising a 3% aqueous sodium chloride solution at a temperature of 5°C. The test was terminated after 2 735 hours and the following information was revealed.

	Period on test (hrs)	0	236	525	885	1 141
10	Loading g/m ²	22.4	21.8	20.8	20.9	19.3

	Period on test (hrs)	1 421	1 732	2 186	2 400	2 735
15	Loading g/m ²	18.6	18.3	17.4	16.9	15.8

Micrographic examination of the sample on termination revealed signs of coating dissolution but no undermining of the coating. A second test was carried out in which 6g/m² of tantalum pentoxide were applied to a sheet of titanium and the titanium was then vacuum heat treated as before. 18.2g of platinum-iridium was then applied by the same process as before and material from that sheet was then tested under identical conditions as set out above. Tests were carried on for a period of 2 132 hours, after which the tests were terminated. The coating loading as measured during the tests is set out below.

at a low temperature is required by many operators, particularly those carrying out operations in the extreme northern and southern hemispheres.

It has also been discovered that the application of a sub-stoichiometric tantalum oxide (ie Ta_2O_n where n is less than 5 but is not necessarily a whole number) interlayer between a platinum group metal outer layer and a titanium substrate leads to dramatic improvements in life when the electrode is operated as an anode in a zinc winning solution. Zinc is conventionally won from an acidified zinc sulphate solution and an electrode manufactured by coating the titanium substrate with $10g/m^2$ of tantalum and subsequently vacuum heat treating the electrode for one hour at $750^\circ C$ with an outer layer of $10g/m^2$ iridium operated satisfactorily in a zinc winning cell. Furthermore it has unexpectedly been discovered that the coating produced by the method outlined above has a smooth surface and such a smooth surface tends to reduce the accretion of manganese dioxide deposits in a zinc electrowinning cell. Manganese ions are conventionally found in commercial zinc winning cells and manganese dioxide tends to be deposited onto the anode interfering with the electrochemical efficiency of the cell. The electrodes in accordance with the present invention operate satisfactorily in zinc winning solutions, have a smooth surface which tends to decrease manganese dioxide accretion and have a satisfactory electrochemical performance. They also have a low wear rate.

The manganese dioxide which does deposit on the anodes in use can be simply removed by rinsing under a continuous flow of water and drying.

Period on test (hrs)	0	257	537	848
Loading g/m ²	18.2	18.1	17.2	15.6

Period on test (hrs)	1 302	1 516	1 851	2 132
Loading g/m ²	14.4	13.1	12.5	12.0

It is particularly significant to compare this latter test with Example A above. It can be seen that in Example A 18.2g/m² of platinum-iridium was present after 714 hours of operation and failure occurred at 1 008 hours. By comparison the provision of the sub-stoichiometric tantalum oxide interlayer produced an electrode which had lost only one third of its coating after 2 132 hours. It will be appreciated, therefore, that a very significant increase in coating durability is obtained and the electrode in accordance with the invention is capable of operating under the extremely arduous conditions of a cold hypochlorite cell in a better manner than any known prior electrode.

It will be realised that although hypochlorite electrolyzers may not be required to operate all the year round with low temperature inlet seawater there will be periods of the year, particularly during the winter, when this is a very desirable requirement.

Although when inlet seawater temperatures are low there is usually less requirement for generation of sodium hypochlorite to restrict bio-fouling, nevertheless the ability of a hypochlorite cell to operate

acid undermining resistance of this coating can be further improved by the application of an undercoating of tantalum oxide partially reduced by heating in a vacuum.

5 Such electroplated products or products in which tantalum oxides are used below platinum group metal coatings are also of use in sodium sulphate electrolysis and in sodium persulphuric cells.

10 It will be further appreciated that other known anodically active coatings, such as lead dioxide or platinum plus 30% iridium coatings, may be applied to the electrodes. In the case of platinum-iridium coatings they may be applied from resins or chloride compounds of the precious metals dissolved
15 in a suitable organic solvent.

Furthermore it is found that there is only a small tendency for the manganese dioxide to build up on the anodes. The deposit tends to fall away in flakes rather than form a hard layer as it does on a lead-silver anode (the conventional anode for zinc winning). The fact that less manganese deposits on the anode results in cleaner cells and a cleaner return acid. Furthermore the lead content of the zinc deposited on the cathode is much less than a quarter of that which is obtained utilising a lead-silver anode. There is a significant improvement in cell operating voltage, particularly when the anodes are new, and there is a slight improvement in cell efficiency. However, even such slight improvements can be significant for large plantoperation purposes. After three months of testing in a zinc cell samples having an initial loading of 10g/m of tantalum oxide and 10g/m of iridium were found to have lost less than 5% of their coating. Thus a life of up to 5 years can be predicted for electrodes in accordance with the present invention. This is significantly better than any other known platinum group metal containing electrode for use in a metal winning cell.

The application of a tantalum underlayer beneath coatings for use in acid environments also improves the acid undermining resistance of the coating. Thus the best known and most acid undermining resistant coating known to date is the coating described in UK Patent Specification 1 351 741. Such a coating essentially comprises a primary layer of platinum which is painted and fired onto the surface onto which is electroplated a further layer of platinum. It has now been discovered that the high

5. A method as claimed in Claim 4 in which the platinum group metal, oxide, alloy or mixture is applied by a route selected from the group:
- i applying a paint containing an organic or inorganic compound of the platinum group metal(s) to the surface and heating in air or an oxygen-containing atmosphere at a temperature in the range 350°C to 650°C to convert the compound to the metal(s) or oxide(s)
 - ii electroplating the platinum group metal onto the oxide layer or onto a previously applied painted and fired platinum group metal layer.
6. An electrode for electrochemical processes comprising a substrate of titanium or an alloy thereof, an intermediate coating of sub-stoichiometric tantalum oxide and an outer layer of anodically active material.
7. An electrode as claimed in Claim 6 in which the anodically active material is a coating containing a platinum group metal or oxide or an alloy or mixture of platinum group metals or oxides.
8. An electrochemical cell including an anode and a cathode surrounded by an electrolyte wherein the anode comprises an electrode manufactured by a method as claimed in any one of Claims 1 to 5 or is an electrode as claimed in Claim 6 or Claim 7.
9. An electrochemical cell as claimed in Claim 8 in which the cell is a hypochlorite cell which in use generates sodium hypochlorite from an aqueous sodium chloride solution, the cell being capable of and adapted for operation at temperatures of 10°C or below.


CLAIMS:

1. A method of manufacturing an electrode for use in an electrolytic cell, which method includes the steps of forming on the surface of a titanium substrate a coating by:
 - 5 i forming a layer of an oxide of a metal chosen from the group titanium, tantalum, zirconium, hafnium and niobium on the titanium surface
 - ii heat treating the layer in a vacuum or in a non-oxidising atmosphere, said atmosphere
10 being substantially hydrogen-free, at a temperature and for a time sufficient for the titanium partially to reduce the oxide,
 - iii applying to the oxide layer a layer of an anodically active material.
- 15 2. A method as claimed in Claim 1 in which the layer of oxide is titanium oxide, deposited on the surface of the titanium by immersing the titanium surface into an acid solution containing trivalent titanium cations, maintaining the solution at a
20 temperature in excess of 75°C and rendering the titanium surface anodic with respect to a cathode to anodically oxidise the titanium cations to form titanium oxide which is deposited onto the titanium surface as an adherent porous titanium oxide layer.
- 25 3. A method as claimed in Claim 1 in which the oxide is tantalum oxide formed by applying a paint of a tantalum-containing compound to the surface and heating the surface in air or an oxygen-containing atmosphere to convert the compound to an oxide of
30 tantalum.
4. A method as claimed in any one of Claims 1 to 3 in which the anodically active coating contains a platinum group metal or oxide or an alloy or mixture of platinum group metals or oxides.

1 / 2

35°C 3330 Am⁻²

FIG. 1.



10. An electrochemical cell as claimed in Claim 8
in which the electrolyte is an acidified sulphate
solution, particularly a solution containing ions of a
metal chosen from the group zinc, copper, nickel or
5 cobalt.

870/rcs/em



European Patent
Office

EUROPEAN SEARCH REPORT

0052986
Application number

EP 81305382.4

DOCUMENTS CONSIDERED TO BE RELEVANT			CLASSIFICATION OF THE APPLICATION (Int. Cl. 7)		
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim			
A	<u>GB - A - 1 231 280</u> (ELECTRONER CORPORATION) * Claims 1-7,12 * --	1,4,7	C 25 B 11/10 C 25 B 1/26 C 25 C 7/02		
D,X	<u>GB - A - 1 327 760</u> (IMPERIAL METAL INDUSTRIES (KYNOC) LIMITED) * Claims 1-5,8; examples 1,3 * --	1,2,4,5,7			
A	<u>CH - A - 563 464</u> (ENGELHARD MINERALS & CHEMICALS CORPORATION) * Claims I,1,2,4,6,7 * --	1	TECHNICAL FIELDS SEARCHED (Int. Cl. 7)		
A	<u>US - A - 4 203 810</u> (MICHAEL A. WARNE) * Claims 1-5,7-9; columns 7,8 * --	1	C 25 B C 25 C C 25 D		
A	<u>US - A - 3 632 498</u> (HENRI BERNARD BEER) * Claims 1-3 * ----	1	CATEGORY OF CITED DOCUMENTS		
<input checked="" type="checkbox"/> The present search report has been drawn up for all claims			X: particularly relevant A: technological background O: non-written disclosure P: intermediate document T: theory or principle underlying the invention E: conflicting application D: document cited in the application L: citation for other reasons		
			8. member of the same patent family. corresponding document		
Place of search	VIENNA	Date of completion of the search	24-02-1982	Examiner	HEIN

